

Preliminary Radiation Studies Proton Irradiation at the PS

Measurements on 2 ASDBLR chips exposed to 10^{14} Protons /cm²
Powered during exposure on a TB3 Board

Summary	Top chip		Bottom chip	
	PRE	POST	PRE	POST
3fC Mean (mV)	456	415	453	426
3fC Sigma (mV)	11.5	33.4	17.7	26.6
30fC Mean (mV)	352	326	351	326
30fC Sigma (mV)	12	11	18	20

